

Hydrophilic Fumed Silica

XYSIL® 200LS is a hydrophilic Fumed Silica with a specific surface area of 220m2/g, and it is synthetic, hydrophilic,

amorphous silica, produced via flame hydrolysis.

Physico-chemical Data

| Properties | Units | Typical Value | Standardization |
|--|-------|---------------|-----------------|
| Specific surface area (BET) | m²/g | 220±15 | GB/T10722 |
| pH-value (in 4% dispersion) | | 3.8-4.5 | GB/T1717 |
| Loss on drying, ex works(2h @ 105℃) | wt% | <1.5 | GB/T5211.3 |
| Loss on ignition(2h @ 1000,based on material dried for 2h @ 105 $^\circ$ C) | wt% | <2.5 | GB/T20020 |
| Sieve residue (45µm) | % | <0.05 | GB/T5211.14 |
| SiO_2 content (based on the substance heated at 1000 $^\circ\!\mathbb{C}$ for 2 h) | wt% | >99.8 | GB/T20020 |
| Tamped density (based on material dried for 2h @ 105 $^\circ$ C) | g/L | 25~60 | GB/T5211.4 |
| Carbon content (based on material dried for 2h @ 105 $^\circ$ C) | wt% | <0.2 | GB/T20020 |

At time of packaging.

Application s and Properties

Application:

- ♦ RTV Silicone Sealant, HTV Silicone Rubber
- ♦ Paints and Coatings, Ink, Pigment
- ♦ Unsaturated polyester resins
- ♦ Adhesive & Sealant
- ♦ Thermal insulation material, Vacuum Insulation Panel
- ♦ Composites& PVC, Storage Battery

Functions:

- Rheology and thixotropy Control of of liquids, binders, polymers, etc.
- ♦ Used as anti-settling, thickening, anti-sagging agent
- ♦ Free Flow and Suspension for Powder
- ♦ Reinforcement in Silicone Rubber

Packing and Storage

XYSIL[®] 200LS is packaged in multiple layer kraft paper 10kg bags on pallet, and should be stored in the original packaging in dry storage areas for protecting the material from volatile substance.

Transportation:

Sea Transportation 20'GP: 1800KG, 10 pallets, 180KG/pallet. 40'GP: 3600KG, 20 pallets, 180KG/pallet. 40'HQ: 4000KG, 20 pallets, 200KG/pallet. Road Transportation: by requirement

This information is supplied on basis of our best knowledge, as a convenience and for information purposes only. We disclaim any warranty and liability whatsoever as to accuracy and completeness of such information as well as to the potential infringement of any proprietary rights.

Henan Xunyu Chemical Co.,Ltd

Add: No.18, Shangwu Waihuan Road, Zhengdong New Dis, Zhengzhou City, Henan Province, P.R. China Tel: +86 371 69176282 Fax: +86 371 69176283 Email: info@xunyuchem.com; technique@xunyuchem.com Website: www.xunyuchem.com



TECHNIQUE DATA SHEET