

XYSIL®R230

Hydrophobic Fumed Silica

TECHNIQUE DATA SHEET

XYSIL [®] **R230** is a Fumed Silica surface-treated with **HMDS(hexamethyldisilazane)** based on a hydrophilic fumed silica with a specific surface area of 300m²/g.

Physico-chemical Data

Properties	Units	Typical Value	Standardization
Specific Surface Area(BET)	m2/g	250±20	GB/T10722
pH Value (in 4% dispersion)		5.5-8.0	GB/T10722
Loss on Drying, Ex Works (2h @ 105℃)	wt%	<0.5	GB/T1717
Loss on ignition(2h @ 1000,based on material dried for 2h @ 105℃)	wt%	<2.0	GB/T5211.3
Tamped density (based on material dried for 2h @ 105℃)	g/L	40~60	GB/T5211.14
SiO2 content(based on the substance heated at 1000 ℃ for 2 h)	wt%	>99.8	GB/T20020
Carbon content(based on material dried for 2h @ 105℃)	wt%	2.0-3.0	GB/T5211.4
Surface modification	Hexamethyldisilazane		

At time of packaging.

Applications and Properties

Application:

Paint&Coating;

Functions:

- Anti-settling;
- Anti-Sagging;
- Corrosion resistance;
- > Rheology control;

Packing and Storage

XYSIL[®] R230 is packaged in multiple layer kraft paper 10kg bags on pallet, and should be stored in the original packaging in dry storage areas for protecting the material from volatile substance.

Transportation:

Sea Transportation

20'GP: 1800KG, 10 pallets, 180KG/pallet. 40'GP: 3600KG, 20 pallets, 180KG/pallet. 40'HQ: 4000KG, 20 pallets, 200KG/pallet. Road Transportation: by requirement

This information is supplied on basis of our best knowledge, as a convenience and for information purposes only. We disclaim any warranty and liability whatsoever as to accuracy and completeness of such information as well as to the potential infringement of any proprietary rights.

Henan Xunyu Chemical Co..Ltd

Add: No.18, Shangwu Waihuan Road, Zhengdong New Dis, Zhengzhou City, Henan Province, P.R. China

Tel: +86 371 69176282 Fax: +86 371 69176283

Email: info@xunyuchem.com; technique@xunyuchem.com

Website: www.xunyuchem.com

Certificated by ISO9001 – ISO14001 – ISO45001 – SGS- REACH – KKDIK – K-REACH