

**XYSIL® 380****Hydrophilic Fumed Silica****TECHNIQUE DATA SHEET**

**XYSIL® 380** is a hydrophilic Fumed Silica with a specific surface area of 380m<sup>2</sup>/g, and it is synthetic, hydrophilic, amorphous silica, produced via flame hydrolysis.

**Physico-chemical Data**

Properties	Units	Typical Value	Standardization
Specific surface area (BET)	m <sup>2</sup> /g	380±25	GB/T10722
pH-value (in 4% dispersion)		3.8-4.5	GB/T1717
Loss on drying, ex works( 2h @ 105℃)	wt%	<2.0	GB/T5211.3
Loss on ignition(2h @ 1000, based on material dried for 2h @ 105℃)	wt%	<2.5	GB/T20020
Sieve residue (45µm)	%	<0.05	GB/T5211.14
SiO <sub>2</sub> content (based on the substance heated at 1000℃ for 2 h)	wt%	>99.8	GB/T20020
Tamped density (based on material dried for 2h @ 105℃)	g/L	25~60	GB/T5211.4
Carbon content (based on material dried for 2h @ 105℃)	wt%	<0.2	GB/T20020

At time of packaging.

**Applications and Properties**

Application:

- ✧ HTV Silicone Rubber
- ✧ Paints and Coatings, Printing Inks
- ✧ Unsaturated polyester resins(UPR)
- ✧ Cable compounds
- ✧ Adhesive & Sealant

Functions:

- ✧ Rheology and thixotropy Control of polymers, liquids, etc
- ✧ The highest surface area resulting in the best thickening and thixotropy
- ✧ Reinforcement of HTV Silicone Rubber
- ✧ High Transparency
- ✧ Flow aid

**Packing and Storage**

XYSIL® 380 is packaged in multiple layer kraft paper 10kg bags on pallet, and should be stored in the original packaging in dry storage areas for protecting the material from volatile substance.

**Transportation:**

Sea Transportation  
 20'GP: 1800KG, 10 pallets, 180KG/pallet.  
 40'GP: 3600KG, 20 pallets, 180KG/pallet.  
 40'HQ: 4000KG, 20 pallets, 200KG/pallet.  
 Road Transportation: by requirement

This information is supplied on basis of our best knowledge, as a convenience and for information purposes only. We disclaim any warranty and liability whatsoever as to accuracy and completeness of such information as well as to the potential infringement of any proprietary rights.

**Henan Xunyu Chemical Co., Ltd**

Add: No.18, Shangwu Waihuan Road, Zhengdong New Dis, Zhengzhou City, Henan Province, P.R. China

Tel: +86 371 69176282 Fax: +86 371 69176283

Email: info@xunyuchem.com; technique@xunyuchem.com

Website: www.xunyuchem.com